



MULTYFILLER GRIP

C36

VERSION: 200605
Page: 1/5

2K ACRYLIC 4:1 DTM PRIMER

DEFINITION

MULTYFILLER GRIP is 2K high solids acrylic primer filler. Its modern formulation, anti-corrosive pigment content and chemical resistance ensure good isolating properties which allows it to be applied directly over a variety of substrates. At the same time emphasizing its versatility of application it has excellent levelling properties and is easy to sand. All these characteristics make **MULTYFILLER GRIP** a perfect base for excellent finishing results. This product is an environmentally friendly product due to its low VOC content.

- High build filler
- Primer Surfacer
- Non sanding

PHYSICAL CHARACTERISTICS







Nature: Acrylic 2K
Colour: G0 - white, G4 - grey, G6 - black
Specific weight: 1,5 kg/l at 20°C

	<i>High build filler</i>	<i>Primer Surfacer</i>	<i>Non sanding</i>	
Dry film thickness:	80 microns	50 microns	15 microns	Per coat
VOC:	444 g/l	514 g/l	504 g/l	Mixing application
Yield:	6 - 7 m ² /l	8 -10 m ² /l	16 - 18 m ² /l	Per coat

AUXILIARY PRODUCTS

P5000 Primer Hardener standard
Q700 Hardener extra fast
NS21 Non sanding convertor and accelerator
S322 Standard thinner

SURFACE PREPARATION

PROCESS		Paint OEM	Cataphoresis (*)	Polyester Putty	Aluminium	Steel	Electrozinc-coated	Polyester
High build filler								
	P240	√	√	√	√	√	√	√
	DA93	√	√	√	√	√	√	√
Primer Surfacer								
	P240-P320	√	√	√	√	√	√	√
	DA93	√	√	√	√	√	√	√
Non sanding								
	P400	√	√	√	√	√	√	√
	DA93	√	√	√	√	√	√	√





(*) There is no need to sand.

It has adhesion on the more popular plastics in the bodywork.

In case of repaired plastics, sand it with P180/P240 before primer application.




In case of primed and non-primed plastics, it is recommended to degrease and do a slight sanding before primer application.

MIXING RATIO






		High build filler		Primer Surfacer		Non sanding	
		Vol	Weight	Vol	Weight	Vol	Weight
	Multyfiller Grip	100	100	100	100	100	100
	P5000	25	17	25	17	55	36
	NS21	-	-	-	-	33	21
	S322	-	-	20	12	-	-
	F/4 at 20°C	50"		21"		16"	
	20°C	30'		30'		20'	
	20°C	5h		5h		-	

Dry film thickness per coat	80 µm	50 µm	15 µm
DTM	√	√	√
Adhesion on plastics (*)	ABS, PP-EPDM, PP-PE-EPDM		





(*) Adhesion on plastic can be altered if the plastic has been treated

		<i>Primer Surfacer fast</i>	
		<i>Vol</i>	<i>Weight</i>
	Multyfiller Grip	100	100
	Q700	60	41
	NS21	33	21
	F/4 at 20°C	21"	
	20°C	15'	
Dry film thickness per coat		50 µm	
DTM		√	
Adhesion on plastics (*)		ABS	

APPLICATION METHOD


		<i>High build filler</i>	<i>Primer Surfacer / Primer Surfacer fast</i>	<i>Non sanding</i>
		1,6 - 1,9 mm	1,3 - 1,4 mm	1,2 - 1,4 mm
		1.8 - 2.2 bar	1.8 - 2.2 bar	1.8 bar
	Coats	2	2	
	68°F	5 -10 min	5 -10 min	
	Coats		0'5 + 2	0'5 + 1
	68°F		-----	-----

DRYING TIMES






	<i>High build filler</i>	<i>Primer Surfacer</i>	<i>Primer Surfacer Fast</i>	<i>Non Sanding</i>
 20°C	5h	5h	45'-1h	(*)
 60°C	30'	30'	---	---
 OC - 80cm	Flash off - 5' Full bake - 7'	Flash off - 5' Full bake - 7'	---	---
 20°C	5 h	5h	45'-1h	Min 15' Max 60'

(*) In case of superficial imperfections, it can be sanded after 1h at 20°C

SANDING

		<i>High build filler</i>	<i>Primer Surfacer / Primer Surfacer Fast</i>	<i>Non Sanding</i>
 ORBIT 3 - 5	INITIAL	P400	P500 or P600	SANDING PAD MICROFINE
	FINAL	P600		

COLOUR TABLE

<i>Grey Choice</i>	<i>Colours</i>	<i>Mixing ratio % weight G0 / G06</i>	<i>Mixing ratio % weight G0 / G4 / G06</i>	<i>Recommended finishes</i>
R1		100:0	100:0:0	White Yellow Orange
R2		90:10	85:15:0	Red
R3		55:45	25:75:0	Light Green, light blue and light grey. Metallic light green, blue, red and grey. Metallic yellow, beige and orange
R4		30:70	0:60:40	Dark green, blue and grey. Metallic dark green, blue and grey
R5		0:100	0:0:100	Black Metallic black

EQUIPMENT CLEANING

Clean with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

*All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.*