










POLYESTER PUTTIES

		APPEARANCE		MIXING			DRYING										
		S.W.						Temp resistance °C	IRON Fe	ZINC Zn	ALUMINIUM Al						
	colour	specific weight kg /liter	packaging Kg/liter	mixing ratio % by weight	potlife at 20° C.	sanding time at 20° C.	sanding time infra red 60°C.	Temp resistance °C	steel	E-coating	galvanized steel	aluminium	aluminium rims	fiberglass	hard plastic	soft plastic	
GAP 00	GAPOL	black	1,83	2kg/1,09l	2%	4-5'	<25'	10'	80 °C	●	●	●	●	●	●	●	
GAP 10	MULTI	off white	1,81	2kg/1,10l	2%	4-5'	<20'	5'	80 °C	●	●	●	●	●	●	●	
GAP 20	FINE	bright white	1,68	2kg/1,19l	2%	4-5'	<15'	10'	80 °C	●			●	●			
GAP 30	LIGHT	green	1,36	1,5kg/1,09l	2%	4-5'	<15-20'	5-10'	80 °C	●	●	●	●	●			
GAP 31	ULTRA LIGHT	azure	1	1kg/1l	1-3%	3-5'	<30'	4'-5'	80 °C	●	●	●	●	●			
GAP 33	EXTRA LIGHT	green	1	3kg/3l	1-3%	3-5'	<30'	4'-5'	80 °C	●	●	●	●	●			
GAP 40	FIBER	amber	1,61	1,8kg/1,11l	2%	4-5'	<20'	10'	80 °C	●				●			
GAP 50	ALU	alu	1,53	2kg/1,30l	2%	4-6'	<20'	10'	80 °C	●	●	●	●	●			
GAP 70	PLASTFILL	anthracite	1,3	1kg/0,75l	1-3%	3-5'	<30'	4'-5'	80 °C						●	●	
DEB 12	PB - SN	dark alu	1,1	1L/1,3kg	1-3%	3-4'	<30'	-	180° C MAX 15'!	●		●	●	●			

SHELF LIFE PUTTY: 18 MONTHS
 SHELF LIFE BPO HARDENER: 12 MONTHS

			
DRY	FROST FREE	NOT IN DIRECT SUNLIGHT	CLOSED CONTAINER

Chemcar Europe NV
 Baarbeek 2
 2070 Zwijndrecht
 België - Belgium
 T: +32 3 234 87 80
 F: +32 3 234 87 89
 info@finixa.com
 www.finixa.com